

TROJAN° DATA SHEET MOTIVE T1275-AES

MODEL T1275-AES

VOLTAGE 12

CAPACITY 124Ah @ 20Hr MATERIAL Polypropylene

BATTERY VRLA AGM / Non-Spillable / Maintenance-Free

COLOR Maroon

WATERING No Watering Required





12 VOLT

PHYSICAL SPECIFICATIONS

BCI	MODEL NAME	TERMINAL TYPE	DIMENSIONS ° INCHES (mm)		WEIGHT LBS. (kg)	HANDLES	INSTALLATION ORIENTATION	
2212			LENGTH	WIDTH	HEIGHT F	a= (aa)		Horizontal
GC12	T1275-AES	M8/AP/LT	12.96 (329)	7.06 (179)	10.96 (278)	85 (39)	Embedded	and Vertical

ELECTRICAL SPECIFICATIONS

VOLTAGE	CRANKING PERFORMANCE		CAPACITY A MINUTES		CAPACITY ^B AMP-HOURS (Ah)					INTERNAL RESISTANCE (m Ω)	SHORT CIRCUIT CURRENT (amps)
10	C.C.A. ^D @0°F	C.A. ^E @32°F	@ 25 Amps	@ 56 Amps	5-Hr	10-Hr	20-Hr	100-Hr	100-Hr	4.2	2020
12	-	-	217	78	95	112	124	141	1.69	4.3	2920

CHARGING INSTRUCTIONS

CHARGER VOLTAGE SETTINGS (AT 77°F/25°C)							
SYSTEM VOLTAGE	12V	24V	36V	48V			
Maximum Charge Current (A)	50% of C ₂₀						
Absorption Voltage (2.40 V/cell)	14.40	28.80	43.20	57.60			
Float Voltage (2.25 V/cell)	13.50	27.00	40.50	54.00			

Do not install or charge batteries in a sealed or non-ventilated compartment. Constant under or overcharging will damage the battery and shorten its life as with any battery.

CHARGING TEMPERATURE COMPENSATION

ADD	SUBTRACT		
0.005 volt per cell for every 1°C below 25°C 0.0028 volt per cell for every 1°F below 77°F	0.005 volt per cell for every 1°C above 25°C 0.0028 volt per cell for every 1°F above 77°F		

OPERATIONAL DATA

OPERATING TEMPERATURE	SELF DISCHARGE		
-40°F to 140°F (-40°C to $+60$ °C). At temperatures below 32°F (0°C) maintain a state of charge greater than 60%.	Less than 3% per month depending on storage temperature conditions		

RECYCLE RESPONSIBLY









STATE OF CHARGE MEASURE OF OPEN-CIRCUIT VOLTAGE


PERCENTAGE CHARGE	CELL	12 VOLT	
100	2.14	12.84	
75	2.09	12.54	
50	2.04	12.24	
25	1.99	11.94	
0	1.94	11.64	


TROJAN T1275-AES PERFORMANCE




PERCENT CAPACITY VS. TEMPERATURE










TERMINAL TYPE



Battery Height with Terminal in Inches (mm) 11.41 (290) Torque Values in-lb (Nm) Connection to M8: 85 - 90 (10 - 11)Connection to AP: 50 - 70 (6 - 8)

- A. The number of minutes a battery can deliver when discharged at a constant rate at 80°F (27°C) and maintain a voltage above 1.75 V/cell. Capacities are
- The amount of nimities a patient year deliver when discharged at a constant rate at 80°F (27°C) and maintain a voltage above 1.75 Vicell. Capacities are based on peak performance.

 The amount of amp-hours (Ah) a battery can deliver when discharged at a constant rate at 80°F (27°C) and maintain a voltage above 1.75 Vicell. Capacities are based on peak performance.
- Dimensions may vary depending on type of handle or terminal. Batteries should be mounted with 0.5 inches (12.7 mm) spacing minimum. C.C.A. (Cold Cranking Amps) - the discharge load in amperes which a new, fully charged battery can maintain for 30 seconds at 0°F (-18°C) at a voltage above 1.2 V/cell.
- E. C.A. (Cranking Amps) the discharge load in amperes which a new, fully charged battery can maintain for 30 seconds at 32°F (0°C) at a voltage above 1.2 CAL Clothoning Analysis the abschales lower in an impersor which a revent in a way and or a control at a 22 Victor. World. This is sometimes referred to as marine craning amps @ 32°F or M.C.A. @ 32°F. Height taken from bottom of the battery to the highest point on the battery. Heights may vary depending on type of terminal. Terminal images are representative only.

- Batteries in storage should be charged when they decline to 75% State of Charge (SOC).
- Weight may vary.















Designed in compliance with applicable BCI, DIN, BS and IEC standards. Tested in compliance to BCI and IEC standards.

